

AD-A153 099

INVESTIGATION OF THE STRUCTURE AND DYNAMICS OF  
ELECTROLYTES IN SOLVENTS U. (U) POLYTECHNIC INST OF NEW  
YORK FARMINGDALE DEPT OF CHEMISTRY S PETRUCCI FEB 85  
ARD-18978. 8-CH DARG29-82-K-0048

1/1

UNCLASSIFIED


F/G 10/3

NL

END

FILMED

DTIC



MICROCOPY RESOLUTION TEST CHART  
NATIONAL BUREAU OF STANDARDS-1963-A

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

MASTER COPY - FOR REPRODUCTION PURPOSES

2

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER <b>ARO 18978.8-CH</b>	2. GOVT ACCESSION NO. <b>N/A</b>	3. RECIPIENT'S CATALOG NUMBER <b>N/A</b>
4. TITLE (and Subtitle) <b>Investigation of the Structure and Dynamics of Electrolytes in Solvents Used for Primary and Secondary Li-Batteries</b>		5. TYPE OF REPORT & PERIOD COVERED <b>Final- 1 March 1982 28 February 1985</b>
7. AUTHOR(s) <b>S. Petrucci</b>		6. PERFORMING ORG. REPORT NUMBER <b>N/A</b>
PERFORMING ORGANIZATION NAME AND ADDRESS <b>Dept. of Chemistry, Polytechnic Inst. of NY Long Island Center, Route 110, Farmingdale, New York 11735</b>		8. CONTRACT OR GRANT NUMBER(s) <b>DAA6/29/82/K0048</b>
CONTROLLING OFFICE NAME AND ADDRESS <b>U. S. Army Research Office Post Office Box 12211 Research Triangle Park, NC 27709</b>		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS <b>N/A</b>
MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		12. REPORT DATE <b>Feb. 1985</b>
		13. NUMBER OF PAGES <b>11</b>
		15. SECURITY CLASS. (of this report) <b>Unclassified</b>
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
DISTRIBUTION STATEMENT (of this Report)  <b>Approved for public release; distribution unlimited.</b>		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)  <b>NA</b>		
18. SUPPLEMENTARY NOTES  <b>The view, opinions, and/or findings contained in this report are those of the author(s) and should not be construed as an official Department of the Army position, policy, or decision, unless so designated by other documentation.</b>		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) <b>Structure, Dynamics, Electrolytes, Li-Batteries</b>		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number)  <b>During the past three years, we have investigated the structure and dynamics of lithium electrolytes dissolved in solvents of low permittivity as ethers and dimethylcarbonate. These systems are highly relevant for the construction of batteries using lithium anodes.</b>		

DTIC  
ELECT  
APR 29 1985  
S  
D

AD-A153 099

DTIC FILE COPY

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE(When Data Entered)

It appeared necessary to offer the electrochemist a detailed knowledge of the electrolyte species present in the electrolyte solutions and the lifetime and structure of these species. This information is essential for an optimum choice of the electrolyte solution to be used for battery planning and construction. To the above end we have used Raman spectra (occasionally), electrical conductance, microwave dielectric relaxation and radio frequency ultrasonic relaxation. [The first two techniques (Raman and conductivity) give information on the species present in a very different concentration range of electrolyte. Microwave dielectric relaxation gives information on the rotation relaxation time of dipolar species in solutions. From calculated parameters as microscopic relaxation time and static permittivity, one can get information on the charge separation and apparent dipole moment of the dipolar species. Ultrasonic relaxation studies the kinetics of formation and dissociation of complex species in solutions in the half time range  $10^{-6}$  to  $\sim 10^{-9}$  seconds. Within these limits the lifetime of the complex species can be estimated.] As shown below, many systems show a significant amount of quadrupoles or dimers present in the solution. Theoretical expression for the formation constant  $K_q$  of dimers and of  $\Delta H_o$ ,  $\Delta S_o$ ,  $\Delta V_T$  and  $\Delta V_s^o$  (namely the enthalpy, entropy, isothermal and adiabatic volume changes) have been calculated from statistical thermodynamic arguments. In particular, a Bjerrum-type theory for association of electrolytes (AB) to dimers (AB)<sub>2</sub> has been developed.

The following systems have been investigated:

- A) Molecular Relaxation of LiAsF<sub>6</sub> in 1,2-Dimethoxyethane.
- B) Molecular Relaxation of Lithium Salts in 2-Methyltetrahydrofuran at 25°C.
- C) Thermodynamics of Dimerization of Lithium Salts in 1,2-Dimethoxyethane.
- D) Kinetics of Complexation of the Macrocycles 18C6 & 12C4 Ethers with LiAsF<sub>6</sub> in 1,2-Dimethoxyethane at 25°C.
- E) Ionic Conductivity & Microwave Dielectric Relaxation of LiAsF<sub>6</sub> and LiClO<sub>4</sub> in Dimethylcarbonate.
- F) Molecular Dynamics & Ionic Associations of LiAsF<sub>6</sub> in 4-Butyrolactone Mixtures with 2-Methyl Tetrahydrofuran.

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE(When Data Entered)

# FINAL REPORT

to

The U.S. Army Research Office  
P.O. Box 12211  
Research Triangle Park, NC 27709-2211  
Attn: Dr. Bernard Spielvogel

Title: "Investigation of the Structure and Dynamics  
of Electrolytes in Solvents Used for Primary  
and Secondary Li-Batteries"

Date: February 1985

US ARO GRANT NO.: DAA6/29/82/K0048

Principal Investigator: S. Petrucci  
Department of Chemistry  
Polytechnic Institute of New York  
Long Island Center, Route 110  
Farmingdale, NY 11735

Accession For	
NTIS GRA&I	<input checked="" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By _____	
Distribution/ _____	
Availability Codes	
Dist	Avail and/or Special
A-1	



## FORWARD

During the past three years, we have investigated the structure and dynamics of lithium electrolytes dissolved in solvents of low permittivity as ethers and dimethylcarbonate. These systems are highly relevant for the construction of batteries using lithium anodes.

It appeared necessary to offer the electrochemist a detailed knowledge of the electrolyte species present in the electrolyte solutions and the lifetime and structure of these species. This information is essential for an optimum choice of the electrolyte solution to be used for battery planning and construction. To the above end we have used Raman spectra (occasionally), electrical conductance, microwave dielectric relaxation and radio frequency ultrasonic relaxation. [The first two techniques (Raman and conductivity) give information on the species present in a very different concentration range of electrolyte. Microwave dielectric relaxation gives information on the rotation relaxation time of dipolar species in solutions. From calculated parameters as microscopic relaxation time and static permittivity, one can get information on the charge separation and apparent dipole moment of the dipolar species. Ultrasonic relaxation studies the kinetics of formation and dissociation of complex species in solutions in the half time range  $10^{-6}$  to  $\sim 10^{-9}$  seconds. Within these limits the lifetime of the complex species can be estimated.] As shown below, many systems show a significant amount of quadrupoles or dimers present in the solution. Theoretical expression for the formation constant  $K_{\text{sub } q}$  of dimers and of  $\Delta H_0$ ,  $\Delta S_0$ ,  $\Delta V_T$  and  $\Delta V_s^\circ$  (namely the enthalpy, entropy, isothermal and adiabatic volume changes) have been calculated from statistical thermodynamic arguments. In particular, a Bjerrum-type theory for association of electrolytes (AB) to dimers  $(AB)_2$  has been developed.

*Additional keywords:*  
*Lithium batteries; Perry Research Laboratories; Lithium Salts.*

## STATEMENTS OF PROBLEMS STUDIED AND SUMMARY OF RESULTS

As stated above, we have tried to give a molecular structural and dynamic description of selected systems potentially relevant to battery construction. The choice of the systems has been discussed with the Fort Monmouth Army Laboratory Staff dedicated to lithium batteries. To date, the systems investigated, and briefly reviewed here, are as follows:

### **A) Molecular Relaxation of $\text{LiAsF}_6$ in 1,2-Dimethoxyethane.**

Audiofrequency electrical conductivity, Raman spectra, radiofrequency ultrasonic absorption, and microwave dielectric permittivity of  $\text{LiAsF}_6$  in the solvent 1,2-dimethoxyethane (DME) are reported. An analysis of the electrical conductivity data reveals the electrolyte to be associated to ion pairs ( $K_A = 1 \times 10^5 \text{M}^{-1}$ ). Raman spectra of the symmetrical stretching mode of  $\text{AsF}_6^-$  suggest the ion to be "spectroscopically free", namely, either unpaired or solvent separated from the cation. Ultrasonic relaxation data are interpreted in terms of the equilibrium  $\text{Li}^+, \text{S}, \text{AsF}_6^- \rightleftharpoons \text{LiAsF}_6$ , (S being a solvent molecule). The equilibrium appears to be heavily shifted toward solvent-separated ion pairs in accord with the information obtained from Raman spectra. In other words, the majority of the electrolyte is associated in the form of a solvent-separated ion pair symbolized by  $\text{Li}^+, \text{S}, \text{AsF}_6^-$ . Microwave dielectric relaxation data can be interpreted as due to the diffusion rotation relaxation of ion pairs. The estimate of the charge-to-charge distance in the ion pairs reinforces the model that the solvent resides between the cation and the anion in the majority of the pairs. The equilibrium is shifted to increase contact pairs, by increasing the electrolyte concentration, in accordance with the law of mass action.

## B) Molecular Relaxation of Lithium Salts in 2-Methyltetrahydrofuran at 25°C

Ultrasonic absorption data are reported in the frequency range 1-7 MHz and 10-500 MHz for the electrolytes  $\text{LiAsF}_6$  and  $\text{LiBF}_4$  and described by a single Debye relaxation for  $\text{LiAsF}_6$  and by two Debye relaxation processes for  $\text{LiBF}_4$ . The observed processes are interpreted by a multistep Eigen type dimerization process leading to contact quadrupoles. In the case of  $\text{LiAsF}_6$  the products are solvent-separated quadrupoles and contact dimers, whereas for  $\text{LiBF}_4$  contact species predominate. Literature data for  $\text{LiClO}_4$  suggest that the dimers are the major species present. Hence, the extent of dimerization process for the three electrolytes seems to follow the order:  $\text{LiAsF}_6 \simeq \text{LiBF}_4 < \text{LiClO}_4$ . Electrical conductance data at  $t = 25.00^\circ\text{C}$  for  $\text{LiAsF}_6$  and  $\text{LiBF}_4$  in 2-methyltetrahydrofuran (2MTHF) are reported. The data in the concentration range  $6 \times 10^{-4}$  -  $1.50 \times 10^{-2}\text{M}$  are interpreted by the Fuoss-Kraus theory of triple-ion formation yielding estimates of the ion-pair formation constant  $K_p$  and triple ion formation constant  $K_T$ . Microwave dielectric complex permittivities in the frequency range 0.8-90 GHz and concentration range 0.02-0.1 M for  $\text{LiAsF}_6$  and  $\text{LiBF}_4$  in 2 MTHF at  $25^\circ\text{C}$  are reported. Two Debye relaxation processes, one related to the solute and one to the solvent, are able to describe the data. The solute relaxation is interpreted as due to the rotational relaxation of ion pairs. From the calculated apparent dipole moments it is surmised that on the average  $\text{LiBF}_4$  pairs exist more as contact species with respect to  $\text{LiAsF}_6$  pairs.

## C) Thermodynamics of Dimerization of Lithium Salts in 1,2-Dimethoxyethane

Electrical conductance data in the concentration range  $10^{-4}$  to  $10^{-2}$  for



$\text{LiBF}_4$  in 1,2-DME are interpreted by the Fuoss-Kraus theory yielding values for the ion-pair and triple-ion formation constants. Complex dielectric permittivities for  $\text{LiBF}_4$  in 1,2-DME at  $25^\circ\text{C}$  in the frequency range 0.9-81 GHz are reported. The data are interpreted by two Debye relaxation processes, one for the solvent and one for the solute. The latter is interpreted as due to the diffusional rotation of the ion pairs. Ultrasonic absorption data for  $\text{LiBF}_4$  in 1,2-DME at  $25^\circ\text{C}$  in the concentration range 0.28-0.55 M and frequency range 10-550 MHz are reported. The data are described by a single Debye relaxation process and are interpreted as due to an ion-pair dimerization equilibrium leading to formation of quadrupoles. Theoretical expression (similar to the ones of Fuoss and Bjerrum for ion pairs) are developed for the dimerization of ion pairs to quadrupoles. To this end, a point dipole-point dipole potential has been used including the mutual dipole orientation. The dependence of  $K_F$  and  $K_{Bj}$  on the dipole-dipole separation distance is illustrated. Further, the thermodynamic increments  $\Delta V_T$ ,  $\Delta S_0$ ,  $\Delta H_0$ , and  $\Delta V_S$  have been calculated. The Fuoss-Kraus expressions for the quadrupole formation constants based on ellipsoidal and two-sphere models for the dipoles have been also used to calculate the parameters  $\Delta V_T$ ,  $\Delta S_0$ ,  $\Delta H_0$ , and  $\Delta V_S$ . The latter quantity  $\Delta V_S$  is compared to the corresponding parameter found during the present and previous ultrasonic research.

#### **D) Kinetics of Complexation of the Macrocycles 18C6 and 12C4 Ethers with $\text{LiAsF}_6$ in 1,2-Dimethoxyethane at $25^\circ\text{C}$**

Ultrasonic relaxation spectra of the systems  $\text{LiAsF}_6$  added to the macrocycles 18C6 or 12C4 ethers, in molar ratio  $R \approx 1$ , in the solvent 1,2-Dimethoxyethane (DME) at  $t = 25^\circ\text{C}$  are reported. The concentration range covered was 0.05 to 0.25M for 18C6 and 0.1 to 0.3M for 12C4. Ancillary electrical conductance data for the same systems in the concentration range

$10^{-4}$  to  $\sim 0.05\text{M}$  at  $25.00^\circ\text{C}$  reveal that the lithium-macrocycle interaction is weak, the conductance data being the same up to  $\sim 10^{-2}\text{M}$ , within experimental error of the one for the electrolyte in DME. Based on a previous work revealing the presence of an outer sphere-inner sphere equilibrium  $\text{LiAsF}_6 \rightleftharpoons \text{LiAsF}_6$ , the present data are interpreted by a mechanism envisaging competition between the above reaction and the complexation scheme  $\text{LiAsF}_6 + \text{C} \rightleftharpoons \text{LiC}, \text{AsF}_6 + \text{S}$  where C is the crown ether. The results for  $\text{LiAsF}_6 + 18\text{C6}$  are compared with previous ones for the system  $\text{LiClO}_4 + 18\text{C6}$  in DME.

### E) Ionic Conductivity and Microwave Dielectric Relaxation

#### of $\text{LiAsF}_6$ and $\text{LiClO}_4$ in Dimethylcarbonate

Audiofrequency electrical conductivity data are reported in the solvent dimethylcarbonate (DMC) at  $25^\circ\text{C}$  in the concentration range  $10^{-4}$  to  $1\text{M}$  for  $\text{LiAsF}_6$  and  $10^{-4}$  to  $0.3\text{M}$  for  $\text{LiClO}_4$ . From  $10^{-4}$  to  $\approx 10^{-2}\text{M}$  the data are interpreted by the Fuoss-Kraus triple-ions theory leading to the values of the ion pair formation constant  $K_p$  and triple ion formation constant  $K_T$ . For the data at higher concentration, it is shown that the change of static permittivity of the solution (due to the presence of solute ion-pairs and other polar species, which increase the polarization of the solution) can account qualitatively for the behavior of the conductance data and their deviation from the Fuoss-Kraus theory. In other words, these deviations are mostly due to changes in permittivity, not accounted for in the conventional treatment of the data, rather than by the failure of the theory, which is better than recognized so far. Introduction of the quadrupole formation constant is necessary, however, for  $\text{LiAsF}_6$  for a more quantitative treatment of the conductance data. Microwave complex permittivities in the concentration range  $0.05\text{M}$  to  $0.3\text{M}$ , frequency range  $\approx 1$  to  $90\text{ GHz}$  are interpreted by two Debye relaxation processes, one due to the

solute and one to the solvent. For  $\text{LiAsF}_6$  the Böttcher plot, (expressing a quantity related to the change of the relaxation strength ( $\epsilon_o - \epsilon_{oo_1}$ ) with the concentration of electrolyte), is nonlinear with the concentration. Correction of the concentration, by postulating the presence of dielectrically apolar dimers linearizes the plot with a quadrupole formation constant of the order of  $K_q \approx 50\text{M}^{-1}$ , although this figure is very tentative. For  $\text{LiAsF}_6$  both rotational relaxation time and the distance separation of the charges as calculated from the apparent dipole moment suggest distances of the order of contact ion pairs. For  $\text{LiClO}_4$  no curvature in the Böttcher plot is visible, suggesting that presence of quadrupoles is not significant for this electrolyte in DMC, a notion already reported in the literature. This is somewhat surprising in view of the ionic association constant to pairs  $K_p$ , being an order of magnitude larger for  $\text{LiClO}_4$  with respect to  $\text{LiAsF}_6$ . The distance separation of the charges, as calculated from the apparent dipole moment of  $\text{LiClO}_4$  suggests presence of contact species.

#### **F) Molecular Dynamics and Ionic Associations of $\text{LiAsF}_6$ in 4-Butyrolactone Mixtures with 2-Methyl Tetrahydrofuran**



Solutions of  $\text{LiAsF}_6$  at 298.2 K were studied by audiofrequency conductance in the concentrations range  $10^{-4}$ - $10^{-2}$  mol  $\text{dm}^{-3}$ , and by radiofrequency ultrasonic absorption in the concentration range 0.05 - 0.5 mol  $\text{dm}^{-3}$ . The solvents employed were mixtures of 4-butyrolactone with 2-methyl tetrahydrofuran varying in compositions from mole fractions  $X_{\text{BL}} = 0.10$  to

$X_{\text{BL}} = 0.75$ . In dilute solutions the audiofrequency conductivity data yield ion association constants which appear to represent both contact and solvent-separated ion pairs for mixtures up to  $X_{\text{BL}} = 0.36$ . At higher  $\text{LiAsF}_6$  concentrations and in solvent mixtures of composition  $X_{\text{BL}} = 0.75$ , and  $X_{\text{BL}} = 0.35$ , the ultrasonic spectrum shows a single relaxation process which again is

attributed to the formation of both contact and solvent separated ion pairs. For  $X_{BL} = 0.10$ , the ultrasonic spectrum is the sum of two Debye relaxation processes identified with the equilibria  $2LiAsF_6 \rightleftharpoons LiAsF_6 \cdots LiAsF_6 \rightleftharpoons (LiAsF_6)_2$ . Section F will be fully described in the next report of June, 1985 of the second Army Grant.

## CONCLUSIONS AND PROJECTIONS

The above studies have revealed that for lithium salts, in media of permittivity  $\epsilon \leq 10$  the following association scheme seems to occur



where B is the ligand (anion),  $Li \cdots B$  and  $LiB \cdots LiB$  the solvent separated ion-pair and solvent separated dimer and  $LiB$  and  $(LiB)_2$  the contact pair and contact dimer respectively. The extent of the reaction to the far right depends on the competing "ligand", namely, the solvent for the same anion, and on the donor ability of the ligand.

So, for instance, in 1,2 DME only reaction (1) above can be studied by ultrasonic relaxation through equilibrium  $Li \cdots B \rightleftharpoons LiB$ , (no evidence of dimers existing). The same electrolyte in 2MTHF, an almost isodielectric solvent to DME, shows evidence of reaction (2) at least up to the formation of  $LiB \cdots LiB$  species.  $LiClO_4$  is so heavily associated in 2MTHF that only the last step of reaction (2)  $LiB \cdots LiB \rightleftharpoons (LiB)_2$  appears to be present.

Further work will be necessary to possibly arrive at meaningful correlations of the association constants with parameters as permittivity and solvent donor number for a given electrolyte. Work at various temperatures and in solvent mixtures is also planned in the next project.

## LIST OF PUBLICATIONS AND TECHNICAL REPORTS

### Publications:

1. "Molecular Relaxation of  $\text{LiAsF}_6$  in 1,2 Dimethoxyethane," by H. Farber, D. Irish and S. Petrucci, *J. Phys. Chem.*, **87**, 3515 (1983).
2. "Molecular Relaxation of Lithium Salts in 2-Methyltetrahydrofuran at 25°C," by M. Delsignore, H.E. Maaser and S. Petrucci, *J. Phys. Chem.*, **88**, 2405 (1984).
3. "Thermodynamics of Dimerization of Lithium Salts in 1,2-Dimethoxyethane," by H.E. Maaser, M. Delsignore, M. Newstein and S. Petrucci, *J. Phys. Chem.*, **88**, 5100 (1984).
4. "Molecular Dynamics and Ionic Association of  $\text{LiAsF}_6$  in 4-Butyrolactone Mixtures with 2-Methyl Tetrahydrofuran," by Y. Harada, M. Salomon and S. Petrucci, *J. Phys. Chem.*, 0000 (1985).
5. "Kinetics of Complexation of the Macrocycles 18C6 and 12C4 Ethers with  $\text{LiAsF}_6$  in 1,2-DME at 25°C," by H. Richman, Y. Harada, and S. Petrucci, *J. Phys. Chem.*, 000 (1985).

### Technical Reports

1. Technical Report #1 (June 1982), "Molecular Relaxation of  $\text{LiAsF}_6$  in 1,2 Dimethoxyethane," by H. Farber, D. Irish and S. Petrucci.
2. Technical Report #2 (December 1982), "Kinetics of Quadrupole Formation of Lithium Salts in 2-Methyltetrahydrofurane," by M. Delsignore, H.E. Maaser and S. Petrucci.
3. Technical Report #3 (June 1983), "Molecular Dynamics of Lithium Salts in 2-Methyltetrahydrofurane." by M. Delsignore, H.E. Maaser and S. Petrucci.

1. Technical Report #4 (December 1983), "Thermodynamics of Dimerization of Lithium Salts in 1,2-Dimethoxyethane," by H.E. Maaser, M. Delsignore, M. Newstein and S. Petrucci.
2. Technical Report #5 (June 1984), "Kinetics of Complexation of the Macrocycles 18C6 and 12C4 Ethers with  $\text{LiAsF}_6$  in 1,2-Dimethoxyethane," by H. Richman, Y. Harada and S. Petrucci.
3. Technical Report #6 (December 1984), "Ionic Conductivity and Microwave Dielectric Relaxation of  $\text{LiAsF}_6$  and  $\text{LiClO}_4$  in Dimethylcarbonate," by M. Delsignore, H. Farber and S. Petrucci.

LIST OF ALL PARTICIPATING SCIENTIFIC PERSONNEL (in alphabetical order)

1. Delsignore, Marta, Post-doctoral, June 1982-June 1983 and August-September 1984, presently at Colgate-Palmolive, Piscataway, NJ.
2. Farber, Herman, Dept. of Electrical Engineering, Polytechnic Institute of New York, Brooklyn Campus, 333 Jay Street, Brooklyn, NY.
3. Harada, Yoshifumi, Post-doctoral, September 1983-September 1984, presently at The Dept. of Applied Physics, University of Fukui, Fukui, Japan.
4. Irish, D.E., University of Waterloo, Ontario, Canada.
5. Maaser, Adrian, Post-doctoral, June 1982-June 1983, presently at Colgate-Palmolive, Piscataway, NJ.
6. Newstein, Maurice, Dept. of Electrical Engineering, Polytechnic Institute of New York, Long Island Center, Route 110, Farmingdale, NY.
7. Petrucci, Sergio, Dept. of Chemistry, Polytechnic Institute of New York, Long Island Center, Route 110, Farmingdale, NY.

8. Richman, Helmut, Research Associate, October-December 1983, presently at the Max-Planck Institute of Biophysical Chemistry, am Fassberg, Goettingen-Nikolausberg, West Germany.
9. Salomon, Mark, U.S. Army ET and DL, Ft. Monmouth, NJ.

Note: Profs. Farber, Irish, Newstein, and Dr. Salomon have contributed to the research program and are co-authors of the published papers. They have not received any financial reward from the contract funds.

**END**

**FILMED**

**6-85**

**DTIC**